

FREQUENTLY ASKED QUESTIONS

PANAVIA™ Veneer LC



What is “PANAVIA™ Veneer LC”?

“PANAVIA™ Veneer LC” is a light-cure adhesive resin cement system. It consists of the “PANAVIA™ Veneer LC” Paste (a light-cure cement paste), “CLEARFIL™ CERAMIC PRIMER PLUS” (a silane, zirconia & metal primer), K-ETCHANT Syringe (Phosphoric Acid), and “PANAVIA™ V5” Try-in Paste. “CLEARFIL™ Universal Bond Quick” or “PANAVIA™ V5” Tooth Primer can be chosen for tooth treatment.

What are the indications?

Cementation of ceramic and composite inlays, onlays and laminate veneers with less than 2 mm thickness of the following materials: silica-based ceramics (e.g. conventional porcelain, lithium disilicate), hybrid ceramics, composite resin and “KATANA™ Zirconia” STML/UTML/YML (with a thickness of less than 1.2 mm).

How can I treat the prosthetic restoration?

Follow the Instructions for Use of the restorative material. In the absence of specific instructions, we recommend the following procedures and application of the provided “CLEARFIL™ CERAMIC PRIMER PLUS”: if the adherent surface is silica-based ceramic (e.g. conventional porcelain, lithium disilicate), hybrid ceramic or composite resin: Based on the type of restoration, hydrofluoric acid etching or air abrasion treatment may be used:

Acid Etching Treatment (e.g. conventional porcelain, lithium disilicate):

Etch the adherent surface with a hydrofluoric acid solution in accordance with the Instructions for Use of the solution. Rinse the adherent surface with water and dry.

Air Abrasion Treatment (e.g. composite resin):

Roughen the adherent surface by blasting with alumina powder (30-50 µm) using air pressure of 0.1-0.2 MPa (1-2 kgf/cm², 15-29 psi, 1-2 Bar). The air pressure and powder size should be properly adjusted to suit the material and/or shape of the prosthetic restoration, using caution to prevent chipping. Clean the prosthetic restoration in an ultrasonic cleaning unit for 2 minutes or with “KATANA™ Cleaner” with 10 seconds of rubbing and then rinse with water.

Is it possible to use “CLEARFIL™ Universal Bond Quick” for the surface treatments of veneer restorations?

Although technically possible, we recommend to use “CLEARFIL™ CERAMIC PRIMER PLUS” to get optimal performance for glass ceramics.

Are there additional steps, if I try-in the restoration after it is acid etched or air abraded?

Yes, doing that would contaminate the restoration and, hence, decrease the bond strength. To remove the contamination, use "KATANA™ Cleaner" for 10 seconds with a rubbing motion then rinse with water until the color has been disappeared and dry the restorations to remove contaminants, or apply K-ETCHANT Syringe (Phosphoric Acid) for 5 seconds in case of non-zirconia restorations.

How can I treat the prepared tooth?

There are 2 ways to treat the prepared tooth: with the "PANAVIA™ V5" Tooth Primer or "CLEARFIL™ Universal Bond Quick".

- a) **"PANAVIA™ V5" Tooth Primer:** Etch the enamel with the K-ETCHANT (phosphoric acid) for 10 seconds, rinse and dry. Apply the Tooth Primer to the entire prepared tooth surface, with an applicator brush and leave it in place for 20 seconds. Thoroughly dry the entire adherent surface sufficiently by blowing mild, oil-free air until all water is evaporated from the primer.
- b) **"CLEARFIL™ Universal Bond Quick":** Selective etch the enamel with K-ETCHANT syringe (phosphoric acid) for 10 seconds, rinse and dry. Apply BOND with a rubbing motion to the entire preparation with the applicator brush. No waiting time is required. Dry the entire cavity wall sufficiently by blowing mild air for more than 5 seconds until BOND does not move.

When cementing laminate veneers, there is no need to light-cure BOND prior to seating the laminate veneers. It should be cured after seating the laminate veneers with the "PANAVIA™ Veneer LC" cement. When cementing inlays or onlays, BOND should be light-cured before seating the restoration. Please confirm the curing time by referencing the Instructions for Use.

What are the differences of using the "PANAVIA™ V5" Tooth Primer or "CLEARFIL™ Universal Bond Quick" when treating the prepared tooth?

In terms of bond strength, both are similar and provide excellent results. Nevertheless, the "PANAVIA™ V5" Tooth Primer will provide a "touch-cure" mechanism that will seal the bonding interface before the final light curing. Additionally, while the application time is shorter with "CLEARFIL™ Universal Bond Quick" (no waiting time versus 20 s), there is a longer working time under ambient light with the "PANAVIA™ V5" Tooth Primer (200 seconds vs 160 seconds with the BOND).

What are the advantages of "PANAVIA™ Veneer LC" over competing products?

PANAVIA™ Veneer LC" offers the ideal paste consistency, not being too high or too low as several competitive products. This will facilitate the dispensing of the paste onto the restoration and smooth seating of such restoration. A low film thickness and long working time are also advantages over competitive products. In addition, in case of using it with the "PANAVIA™ V5" Tooth Primer, the "touch-cure" mechanism will provide bonding interface sealing.

How should the excess cement be removed?

One of the following two techniques can be used:

Tack-Cure Clean-Up Technique: Light-cure any excess cement in several spots for 1 second at a distance of 10-15 mm. Hold the prosthetic restoration in position, remove the tack-cured excess cement using a dental instrument.

Wet Clean-Up Technique: Any excess cement remaining at the margins can be removed with a small brush, foam pellet, dental floss or dental explorer.

Regardless of the technique used, final curing will be required as the next step. Please refer to the Instructions for Use.

Should the margins be covered with a protective gel during final curing?

The use of a protective gel, like "PANAVIA™ F 2.0" OXYGUARD II, is beneficial to prevent the forming of an oxygen inhibited layer thus helping to create smooth margins.

How many shades of "PANAVIA™ Veneer LC" Paste are available?

There are 4 shades of "PANAVIA™ Veneer LC" Paste available: Clear, Universal (A2); White and Brown (A4). Each shade has a corresponding glycerin based, water soluble Try-In Paste.

How is the "PANAVIA™ V5" Try-in Paste used?

The "PANAVIA™ V5" Try-In Paste shades match the "PANAVIA™ Veneer LC" shades (in light-cured state) and allow for a simulation of the final appearance of the restoration. The "PANAVIA™ V5" Try-In Paste cannot be (light) cured, and can be removed easily with water.

Is "PANAVIA™ Veneer LC" color stable?

Yes, "PANAVIA™ Veneer LC" Paste is color stable.

What makes "PANAVIA™ Veneer LC" color stable?

Since "PANAVIA™ Veneer LC" Paste is only light curing, no amine reducing agent based redox curing system is included avoiding unwanted discoloration over time.

What is the filler load and particle size?

The total amount of inorganic filler is approximately, 66 wt%, 47 vol%. The particle size of inorganic fillers range from 0.05 µm to 8 µm.

What is the main filler form of "PANAVIA™ Veneer LC"?

"PANAVIA™ Veneer LC" Paste has spherical silica and nano cluster fillers. This provides a paste which is not runny, has excellent handling, and resistance to sagging.

What is the film thickness of "PANAVIA™ Veneer LC"?

"PANAVIA™ Veneer LC" Paste film thickness is around 8 µm.

Can "PANAVIA™ Veneer LC" be used to cement zirconia veneers and inlays/onlays?

Zirconia should not be used because it may not have sufficient translucency. However, zirconia of our products with high translucency ("KATANA™ Zirconia" STML/UTML, "KATANA™ Zirconia" Block STML) can be used with a thickness of less than 1.2 mm.

How is the bond strength of "PANAVIA™ Veneer LC"?

"PANAVIA™ Veneer LC" has excellent bond strength to several substrates (e.g. enamel, dentin, lithium disilicate, "KATANA™ Zirconia", feldspar ceramic) at a similar level to the acclaimed "PANAVIA™ V5".

How many treatments can be cemented with a single syringe?

Approximately 20-30 teeth for laminate veneer.

Do “CLEARFIL MAJESTY™ ES Flow” and “PANAVIA™ Veneer LC” use the same application tips?

No, the “PANAVIA™ Veneer LC” Paste tips are specially designed for an easy extrusion and application and their gauge, which is 16 (1.65 mm in diameter) and differ from the “CLEARFIL MAJESTY™ ES Flow” ones.

How do I store “PANAVIA™ Veneer LC”?

The product should be stored in the refrigerator. All components stored in the refrigerator should be brought to room temperature for 15 minutes before use in order to restore its normal viscosity and curing properties.

What is the shelf-life of the “PANAVIA™ Veneer LC” components?

The shelf-life of “PANAVIA™ Veneer LC” components is 36 months from date of manufacture with refrigeration.



EU Importer
Kuraray Europe GmbH
 Philipp-Reis-Strasse 4,
 65795 Hattersheim am Main, Germany
 Phone +49 (0)69 305 35 835
 Fax +49 (0)69 305 98 35 835
 www.kuraraynoritake.eu
 centralmarketing@kuraray.com

- Before using this product, be sure to read the Instructions for Use supplied with the product.
- The specifications and appearance of the product are subject to change without notice.
- Printed color can be slightly different from actual color.

“PANAVIA” and “CLEARFIL” are trademarks or registered trademarks of KURARAY CO., LTD
 “KATANA” is a trademark or registered trademark of NORITAKE CO., LTD.

